

**KÖSTER**

**Technical guideline / Article number 6.14**

## KB-Pur® IN 2 Injection Resin

Issued: 01<sup>st</sup> of November 2005 Draft

- Industry classification "KB-Pur" registered at the German patent office, 395 06 701
- Official test certificate, Institute for Hygiene, Gelsenkirchen – „Cold water test“ sealing of large and small areas

### Elastic 2 component polyurethane injection resin

#### Features

KÖSTER KB-Pur® IN 2 is a solvent-free, 2 component polyurethane injection resin for crack injection. It is permanently elastic and allows thus a permanent crack and joint sealing even in case of movement of the crack.

KÖSTER KB-Pur® IN 2 is tested according to KTW-recommendations and can thus be used for applications in drinking water environments.

#### Technical data

|                               |           |                 |              |
|-------------------------------|-----------|-----------------|--------------|
| Mixing ratio                  | by volume | Component A : B | 2 : 1        |
|                               | by weight | Component A : B | 5 : 3        |
| Viscosity (A + B component)   |           | approx.         | 200 mPa.s    |
| Pot life (20 °C, 1 l mixture) |           |                 | 30 min       |
| Shore-hardness D / DIN 53505  |           |                 | 25 – 35      |
| Application temperature       |           |                 | above + 5 °C |
| Density (of the mixture)      |           | approx.         | 1.1 kg / l   |

#### Field of application

The material can be used in combination with KÖSTER KB-Pur® IN 1 for the permanent, elastic sealing of water bearing cracks and joints in concrete, screeds, masonry etc. as well as for solidifying granular soils.

It can be used without pre-injections of KÖSTER KB-Pur® IN 1 for closing dry cracks, joints and voids. KÖSTER KB-Pur® IN 2 is used in cases where future movements of the building structure can not be excluded. Also suited for slightly moist cracks.

#### Application

Water bearing cracks, joints and voids are dried up through injections of KÖSTER KB-Pur® IN 1. The placement of the injection packers depends on the course of the crack. The boreholes are best placed on alternating sides of the crack at a distance of approx. 10 to 15 cm of each other at an angle of 45 ° to the surface of the structural member. The diameter of the boreholes depends on the injection packers chosen. All customary

resin injection systems are suited. Prior to the injection, the crack is closed with KÖSTER KB-Fix 5. The two components of KÖSTER KB-Pur® IN 2 are mixed thoroughly using a slowly rotating stirring device. To avoid defects due to insufficient mixing, replot the material and mix it again.

The injection is carried out using customary injection devices, e. g. hand lever presses, from bottom to top.

After the removal of the injection packers, the boreholes can be closed with KÖSTER KB-Fix 5.

#### Consumption

Approx. 1.1 kg / l void

#### Cleaning of tools

Immediately after use with KÖSTER KB-Pur® Cleaner. Reacted material can be treated with KÖSTER KB-Pur® Remover.

#### Packaging

40 kg, 8 kg and 1 kg combi packages

#### Storage

In originally sealed packages at temperatures between 10 and 30 °C, the material can be stored for approx. 12 months.

#### Safety

Wear protective gloves and goggles.

#### Technical guidelines cited

|                                    |          |       |
|------------------------------------|----------|-------|
| KÖSTER KB-Fix 5                    | Art. Nr. | 5.015 |
| KÖSTER KB-Pur® IN 1 Injection Foam | Art. Nr. | 6.13  |
| KÖSTER KB-Pur® Cleaner             | Art. Nr. | 9.10  |
| KÖSTER KB-Pur® Remover             | Art. Nr. | 9.11  |

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.