

## KÖSTER Betomor<sup>®</sup> C-Coat

Tech. guideline / Article Number **5.21**  
Issued: August 25, 2009

Industry classification "Betomor" registered at the German patent office, Nr. 306 07 698

### Filling and levelling mortar as well as shrinkage or blow-hole filler for concrete surfaces

#### Features

KÖSTER Betomor<sup>®</sup> C-Coat is a polymer modified levelling mortar for smoothing standard and visible concrete surfaces. It cures tension free and is waterproof.

#### Technical data

Density of the fresh mortar	1.7 kg / l
Compressive strength (7 days)	> 11 N / mm <sup>2</sup>
Compressive strength (28 days)	> 20 N / mm <sup>2</sup>
Flexural tensile strength (7 days)	> 3 N / mm <sup>2</sup>
Flexural tensile strength (28 days)	> 6 N / mm <sup>2</sup>
Minimum processing temperature	+ 5 °C
Pot life	approx. 45 min

#### Field of application

KÖSTER Betomor<sup>®</sup> C-Coat is suited for filling shrinkage or blow holes on pre-cast concrete parts, for repairing voids in visible concrete surfaces, walls and floors made of concrete as well as bonding and repair-filler for concrete, screed and plaster.

#### Substrate preparation

The substrate has to be solid and sound, free of dust as well as loose particles, free of oil and grease. Strongly absorbent substrates have to be primed with KÖSTER Polysil<sup>®</sup> TG 500. After a setting time of 2 hours, KÖSTER Betomor<sup>®</sup> C-Coat can be applied.

#### Mixing

Do not prepare more material than can be applied within approx. 30 minutes. The maximum processing time is approx. 45 minutes. One 25 kg bag of KÖSTER Betomor<sup>®</sup> C-Coat is mixed with 7 l of clean potable water. First, put the water in a clean mixing vessel.

Then add the powder in portions while continually mixing with a slow rotating (approx. 400 rpm) mechanical mixer until a smooth lump free consistency is reached.

#### Application

KÖSTER Betomor<sup>®</sup> C-Coat is applied with a trowel in one step. As soon as the material starts to set, the surface can be smoothed with a felt board or with a piece of polystyrene foam. Layer thickness: 0 to 5 mm.

#### Consumption

Approx. 1.7 kg / m<sup>2</sup> and mm thickness

#### Cleaning of tools

Clean tools immediately after use with water.

#### Packaging

25 kg bag

#### Storage

Store the material dry; in originally sealed packages, it can be stored for approx. 6 months.

#### Safety

Wear protective gloves and goggles when processing the material.

#### Technical guidelines cited

KÖSTER Polysil<sup>®</sup> TG 500

Art. No. 4.011

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.